

PU Injection Resins

WEBAC® B14

- ▶ WEBAC® B14 is an accelerator for reducing pot life and curing time specially at low temperatures, highly recommended in the cold season.

Range of application

- Accelerates the reaction of PU injection resins **WEBAC. 1403, WEBAC. 1403P and WEBAC. 1405**
- Recommended at low temperatures

Application instructions

- Add accelerator amount referring to total volume (**component A + B**)
- Mix with **component A** immediately before use

WEBAC-Chemie GmbH
 Fahrenberg 22
 22885 Barsbüttel
 Germany
 Tel. +49 40 67057-0
 Fax +49 40 6703227
 info@webac.de

www.webac.de

Technical data

Pot life at 10 °C / 50 °F

		Values		
		WEBAC. 1403	WEBAC. 1403P	WEBAC. 1405
without B14	10 °C	≈ 240 min	≈ 140 min	≈ 95 min
	5 °C	≈ 260 min	≈ 165 min	≈ 130 min
0.5% B14	10 °C	–	≈ 60 min	≈ 45 min
	5 °C	–	≈ 70 min	≈ 55 min
1.0% B14	10 °C	≈ 150 min	≈ 40 min	≈ 30 min
	5 °C	≈ 175 min	≈ 55 min	≈ 30 min
1.5% B14	10 °C	≈ 85 min	≈ 30 min	–
	5 °C	–	≈ 35 min	–
2.0% B14	10 °C	≈ 60 min	≈ 25 min	≈ 15 min
	5 °C	≈ 75 min	≈ 30 min	≈ 20 min
2.5% B14	10 °C	≈ 40 min	≈ 15 min	≈ 10 min
	5 °C	–	–	–
3.0% B14	10 °C	≈ 35 min	≈ 10 min	≈ 5 min
	5 °C	≈ 45 min	≈ 15 min	≈ 15 min
4.0% B14	10 °C	≈ 20 min	–	–
	5 °C	≈ 30 min	–	–
5.0% B14	10 °C	≈ 10 min	–	–
	5 °C	≈ 20 min	–	–

5 °C ≙ 41 °F
 10 °C ≙ 50 °F

The specified data are values determined under laboratory conditions and are subject to a certain fluctuation. Deviations are possible in practice depending on the respective object situation.

Options for acceleration of other PU injection resins on request.

▶ Technical Information

All the data indicated in this technical data sheet and any related information provided by our employees are of an advisory nature representing our current state of knowledge and in no way binding. As the exact chemical, technical and physical conditions of the actual application are beyond WEBAC's control, this information does not preclude examination of the products and/or procedures for the intended application and surface by the user. WEBAC is thus unable to guarantee results. The user is fully responsible for the observation of existing regulations and conditions when using the products.
 © WEBAC-Chemie GmbH. Version 03/17

PU Injection Resins

WEBAC® B14

Product data

	Unit
Packing	5 kg
	1 kg
Storage	<ul style="list-style-type: none"> • Between 5 °C / 41 °F and 30 °C / 86 °F • Protect from moisture • In original, sealed containers



Occupational safety

The safety regulations of the industrial trade associations and the WEBAC Safety Data Sheets are to be observed at all times when working with this product. Safety data sheets according to Regulation (EC) No. 1907/2006 (REACH) must be accessible to all persons responsible for occupational safety, health protection and the handling of materials. For further information, please see the separate information sheet "Occupational Safety" in our product catalog or www.webac-grouts.com.



Waste disposal

In Germany, empty containers can be disposed of via "Interseroh Dienstleistungs GmbH" observing the respective terms and conditions. It is not possible to dispose of containers at production facilities or delivery warehouses. For more detailed information, please see the separate information sheet "Information on the disposal and return of WEBAC packaging" in our product catalog or www.webac-grouts.com and the safety data sheets.

WEBAC-Chemie GmbH
 Fahrenberg 22
 22885 Barsbüttel
 Germany
 Tel. +49 40 67057-0
 Fax +49 40 6703227
info@webac.de

www.webac.de

Technical Information

All the data indicated in this technical data sheet and any related information provided by our employees are of an advisory nature representing our current state of knowledge and in no way binding. As the exact chemical, technical and physical conditions of the actual application are beyond WEBAC's control, this information does not preclude examination of the products and/or procedures for the intended application and surface by the user. WEBAC is thus unable to guarantee results. The user is fully responsible for the observation of existing regulations and conditions when using the products.
 © WEBAC-Chemie GmbH. Version 03/17